

CE DECLARATION OF PERFORMANCE

According to the regulation (EU) Nr. 305 of the European Parliaments and of the Council of 09. March 2011

No.: DoP-0734/06-10 rev.01

1. Type:

OSB/3, thickness 6 - 10 mm

2 Recipe no.:

Rec. 734

3. Intended use:

Structural components for use under dry and humid conditions,
type OSB/3 acc. to EN 300:2006

4. Trade name :

EGGER OSB 3 E0

Manufacturer:

**EGGER Holzwerkstoffe Wismar
GmbH & Co. KG
Am Haffeld 1
D-23970 Wismar**

5. not applicable

6. System of assessment and verification of constancy of performance acc. to Annex V of regulation (EU) No 305/2011:

System 2+

7. Construction product covered by :

EN 13986:2004+A1:2015

Notified body of the EU:

0765

Wilhelm-Klauditz-Institut (WKI)

Bienroder Weg 54 e

D-38108 Brunswick

performed the initial inspection of the manufacturing plant and of the factory production control and the continuous surveillance,
assessment and evaluation of factory production control acc. to EN 13986:2004+A1:2015 System 2+
and issued the certificate of conformity of the factory production control:

353

8. not applicable

9. Declared Performance:

Essential characteristics	Performance			Harmonised technical specification
Thickness range	6 – 10 mm			EN 13986:2004+A1:2015
Panel direction	0° (major axis)	90°(minor axis)		
Strength (N/mm²)				
- Bending	18,0	9,0		
- Compression	15,9	12,9		
- Tension	9,9	7,2		
- Panel Shear	6,8	6,8		
- Planar Shear	1,0	1,0		
Mean Stiffness (N/mm²)				
- Bending	4930	1980		
- Compression	3800	3000		
- Tension	3800	3000		
- Panel Shear	1080	1080		
- Planar Shear	50	50		
Density	≥600 kg/m ³ (determined)			
Punching shear (N/mm²)	NPD			
Reaction to fire	D-s2,d0			
Impact resistance	t≥9mm: Pass			
Water vapour permeability (dry/wet)	200/150			
Air permeability	NPD			
Release of formaldehyde	E 1			
Release of PCP	< 3ppm			
Airborne sound insulation (surface mass)	NPD			
Sound absorption	0,10 / 0,25			
Thermal Conductivity λ	0,13 W/(m*K)			
Racking resistance	EN 1995-1-1			
Embedment strength	EN 1995-1-1			
Durability				
- Internal Bond	0,34 N/mm ²			
- Swelling in thickness	15%			
- Internal Bond Option 1	0,18 N/mm ²			
- Mechanical		kmod =	kdef =	
	SC 1	EN 1995-1-1,	EN 1995-1-1,	
	SC 2	Tab. 3.1	Tab. 3.2	
- Biological	Use class 2			
Performance Floor	Load category	thickness	c-c-span	
EN 12871, OSB 0° major axis	A	NPD		
Performance Roof	Load category	thickness	c-c-span	
EN 12871, OSB 0° major axis	H	NPD		

10. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 9. This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed for and on behalf of the manufacturer by:

Erich Macala
Managing Director Production

Stefan Jacobs
Managing Director Sales